




**DOLLARO**

# DOLLARO



**elli** **professione**  
LEATHER|CONSULTING

[www.professionepelli.com](http://www.professionepelli.com)



## Caratteristiche

**Origine:** Bovine europee

**Concia:** Concia al cromo e riconcia al cromo

**Tintura:** Tintura passante in botte con aniline solide alla luce

**Look:** Vitellone smerigliato stampa dollaro per pelletteria

**Spessore:** 1,3/1,5 mm

**Rispetto delle regolamentazione sulle specifiche protette:** Convenzione di Washington

## Proprietà

Tenuta ad umido 250 cicli

Tenuta a secco 500 cicli

Tenuta al sudore alcalino 80 cicli

Resistenza alla luce

## Prestazioni

Scala dei grigi min. 3-4

Scala dei grigi min. 4

Scala dei grigi min. 3-4

Scala dei blu min. 5

## Technical features

**Raw Origin:** European bovines

**Tannage:** Tanning and re-tanning with chrome

**Dyeing:** Drum-Dyed trough with U.V. resistant anilines

**Look:** Dollar print buffed calfskin for leather goods

**Thickness:** 1,3/1,5 mm

**Respect of regulations on endangered species:** Washington Convention

## Property

Rubbing fastness 250 wet cycles

Rubbing fastness 500 dry cycles

Rubbing fastness 80 sweat cycles

Light fastness

## Performance

Grey scale method min. 3-4

Grey scale method min. 4

Grey scale method min. 3-4

Blu scale method min. 5