



OREGON

OREGON



elli **professione**
LEATHER|CONSULTING

www.professionepelli.com



Caratteristiche

Origine: Bufalo Indiano

Concia: Concia al cromo e riconcia al cromo

Tintura: Tintura passante in botte con aniline solide alla luce

Look: Nabuk cerato con grana naturale

Spessore: 1,3/1,5 mm

Rispetto delle regolamentazione sulle specifiche protette: Convenzione di Washington

Proprietà

Tenuta ad umido 20 cicli

Tenuta a secco 50 cicli

Tenuta al sudore alcalino 20 cicli

Resistenza alla luce

Prestazioni

Scala dei grigi min. 3

Scala dei grigi min. 3

Scala dei grigi min. 3

Scala dei blu min. 3

Technical features

Raw Origin: Indian Buffalo

Tannage: Tanning and re-tanning with chrome

Dyeing: Drum-Dyed trough with U.V. resistant anilines

Look: Waxed nabuk with natural grain

Thickness: 1,3/1,5 mm

Respect of regulations on endangered species: Washington Convention

Property

Rubbing fastness 20 wet cycles

Rubbing fastness 50 dry cycles

Rubbing fastness 20 sweat cycles

Light fastness

Performance

Grey scale method min. 3

Grey scale method min. 3

Grey scale method min. 3

Blu scale method min. 3