




**PULL-UP**

# PULL-UP



**elli** professione  
LEATHER|CONSULTING

[www.professionepelli.com](http://www.professionepelli.com)



## Caratteristiche

**Origine:** Bufalo Indiano

**Concia:** Concia al cromo e riconcia al cromo

**Tintura:** Tintura passante in botte con aniline solide alla luce

**Look:** Nabuk cerato con grana naturale

**Spessore:** 1,2/1,4 mm

**Rispetto delle regolamentazione sulle specifiche protette:** Convenzione di Washington

## Proprietà

Tenuta ad umido 20 cicli

Tenuta a secco 50 cicli

Tenuta al sudore alcalino 20 cicli

Resistenza alla luce

## Prestazioni

Scala dei grigi min. 3

Scala dei grigi min. 3

Scala dei grigi min. 3

Scala dei blu min. 3

## Technical features

**Raw Origin:** Indian Buffalo

**Tannage:** Tanning and re-tanning with chrome

**Dyeing:** Drum-Dyed trough with U.V. resistant anilines

**Look:** Waxed nabuk with natural grain

**Thickness:** 1,2/1,4 mm

**Respect of regulations on endangered species:** Washington Convention

## Property

Rubbing fastness 20 wet cycles

Rubbing fastness 50 dry cycles

Rubbing fastness 20 sweat cycles

Light fastness

## Performance

Grey scale method min. 3

Grey scale method min. 3

Grey scale method min. 3

Blu scale method min. 3