



SOFTY

SOFTY



www.professionepelli.com



Caratteristiche

Origine: Bovine europee

Concia: Concia al cromo e riconcia al cromo

Tintura: Tintura passante in botte con aniline solide alla luce

Look: Articolo mezzofiore asciugato al sottovuoto con stampa fine

Spessore: 0,9/1,1 mm

Rispetto delle regolamentazione sulle specie protette: Convenzione di Washington

Proprietà

Tenuta ad umido 250 cicli

Tenuta a secco 500 cicli

Tenuta al sudore alcalino 80 cicli

Resistenza alla luce

Prestazioni

Scala dei grigi min. 3-4

Scala dei grigi min. 4

Scala dei grigi min. 3-4

Scala dei blu min. 5

Technical features

Raw Origin: European bovines

Tannage: Tanning and re-tanning with chrome

Dyeing: Drum-Dyed trough with U.V. resistant anilines

Look: Half-grain item vacuum dried with fine print

Thickness: 0,9/1,1 mm

Respect of regulations on endangered species: Washington Convention

Property

Rubbing fastness 250 wet cycles

Rubbing fastness 500 dry cycles

Rubbing fastness 80 sweat cycles

Light fastness

Performance

Grey scale method min. 3-4

Grey scale method min. 4

Grey scale method min. 3-4

Blu scale method min. 5